



## ALPINE EWP 661

### *pH Regulator for Soaking Operations*

|                                 |   |
|---------------------------------|---|
| <b>Appearance</b>               | : Beige coloured powder                             |
| <b>Characteristics</b>          | : Mixture of salts and alkaline earth mineral oxide |
| <b>pH Value (10 % in water)</b> | : 10,0 - 12,0                                       |

### **PROPERTIES AND APPLICATION:**

- Alpine EWP 661 is a material which allows the pH to rise gradually remaining at an optimum level until the end of soaking. Does not require control after processing. It is also suitable for soaking process of high-fat bovine leather.
- Optionally can be used mixing with other products. In soaking stage can be applied by alone or combined with sodium sulfite, sodium hydroxide or sodium carbonate in a controlled manner to adjust pH.
- If leather that will be soaking is too oily, the amount of usage should be increased. All rates are based on pelt weight. After 1 hour, the pH must remain constant.
- It is not suitable for use as basification agent in tanning and retanning process.

Recommended usage rates:

|  |             |
|--|-------------|
| When used alone for stabilizing the pH around 10,0 | 0,3 – 0,5 % |
| When combined with other alkaline products         | 0,1 – 0,2 % |

### **STORAGE :**

In a cool and dry place in original packaging, can be stored for a period of one year. Product must be protected from excessive heat and cold.

### **PACKAGING :**

25 kg bag.

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.

**FARBEN DERİ TEKSTİL KONFEKSİYON ve KİMYEVİ MAD. TİC. Ve SAN. A.Ş.**

Organize Deri Sanayi Bölgesi 19. Yol 12/6 Parsel Aydınlı Köyü – Tuzla – İSTANBUL / TURKEY

Tel: +90 216 394 11 25 Fax: +90 216 394 11 24

E-mail: [info@farben.com.tr](mailto:info@farben.com.tr), [info@herkimgroup.com](mailto:info@herkimgroup.com)