



ALPINE CR 6

Auxiliary Substance Preventing Cr (+6) Formation in the Leather

Appearance	: White-thin powder
Characteristics	: Combination of organic and inorganic materials
pH Value (1% in water)	: 2,5 – 3,5
Ionic Structure	: Anionic

PROPERTIES AND APPLICATION :

- It is used in all types of chrome leather. Reduces the risk of Cr (+6) formation on the leather.
- The use of synthetic and vegetable tannins has a preventive effect on the formation of Cr (+6).
- The use of ammonia should not be preferred as it contributes to the formation of Cr (+6).
- It has a protective feature against oxidation hazard that may occur in all types of chrome leather and fur-suede processes.
- It can also be used in lubrication and retanning baths.
- Rinse should not be done after using Alpine CR-6.

Recommended usage rates:

After the fixation process in the leather process, in the last washing bath at 20 - 30 ° C, at 50 - 150% flote rates, Alpine CR-6 is used at rates 1.0 - 2.0% by shaved weight. The processing time should be between 30 and 60 minutes.

STORAGE :

In a cool and dry place in original packaging, can be stored for a period of two years. Product must be protected from excessive heat and cold.

PACKAGING :

25 kg bag.

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.

FARBEN DERİ TEKSTİL KONFEKSİYON ve KİMYEVİ MAD. TİC. Ve SAN. A.Ş.

Organize Deri Sanayi Bölgesi 19. Yol 12/6 Parsel Aydınlı Köyü – Tuzla – İSTANBUL / TURKEY

Tel: +90 216 394 11 25 Fax: +90 216 394 11 24

E-mail: info@farben.com.tr, info@herkingroup.com