



## ALPINE RCA 460

### *Retanning Agent*

<b>Appearance</b>	: Light green powder
<b>Characteristics</b>	: Aluminium-chrome tanning agent
<b>Al<sub>2</sub>O<sub>3</sub> (%)</b>	: 14,0 ± 0,5
<b>Cr<sub>2</sub>O<sub>3</sub> (%)</b>	: 3,0 ± 0,5
<b>pH Value (10 % in water)</b>	: 3,0 - 4,0

### **PROPERTIES AND APPLICATION:**

- It is obtained nearly white leather when Alpine RCA 460 used alone for tanning. Yellowness in tanning that made using aluminium is not observed with this product.
- Alpine RCA 460 gives firmness to the skin, improves dyeing and helps. Because of this property is obtained well-suede and nappa.
- When used in fur tanning, without the formation of green color in feathers, colorless and clear colored suede is obtained.

Recommended usage rates:

In retanning of chrome leather, depending on leather type and thickness of shaved on the shaved weight;  
3,0 – 8,0 %

### **STORAGE :**

In a cool and dry place in original packaging, can be stored for a period of one year. Product must be protected from excessive heat and cold.

### **PACKAGING :**

25 kg bag.

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.

**FARBEN DERİ TEKSTİL KONFEKSİYON ve KİMYEVİ MAD. TİC. Ve SAN. A.Ş.**

Organize Deri Sanayi Bölgesi 19. Yol 12/6 Parsel Aydınlı Köyü – Tuzla – İSTANBUL / TURKEY

Tel: +90 216 394 11 25 Fax: +90 216 394 11 24

E-mail: [info@farben.com.tr](mailto:info@farben.com.tr), [info@herkimgroup.com](mailto:info@herkimgroup.com)