



## ALPINE RSM 335

### *Polymeric Retanning Agent*

<b>Appearance</b>	: Light yellow, fluid liquid
<b>Characteristics</b>	: Styrene-maleic resin
<b>Concentration (%)</b>	: 30,0 ± 1,0
<b>pH Value (10% in water)</b>	: 8,0 – 9,0

### **PROPERTIES AND APPLICATION:**

ALPINE RSM 335 is used for retannage of all types of chrome tanned leather.

Due to the special materials in the structure while filling skin, protects its natural flexibility and softness.

It improves the fixation of the chrome.

It can be used with anionic retannage materials such as dyestuffs, syntans, vegetable tannins, anionic fatliquors. When combined with syntans and metallic tanning salts, its fullness and firmness effect increases.

It may be used immediately after neutralization or in retanning, before or after fatliquoring.

### **Recommended usage rates:**

Depending on the desired effects of fullness;

After neutralization of chromed leather 2,0 – 3,0 %

After dyeing with fatliquoring agent and chrome salt 3,0 – 6,0 %

### **STORAGE :**

In a cool and dry place in original packaging, can be stored for a period of one year. Product must be protected from excessive heat and cold.

### **PACKAGING :**

120 kg drums circle.

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.

**FARBEN DERİ TEKSTİL KONFEKSİYON ve KİMYEVİ MAD. TİC. Ve SAN. A.Ş.**

Organize Deri Sanayi Bölgesi 19. Yol 12/6 Parsel Aydınlı Köyü – Tuzla – İSTANBUL / TURKEY

Tel: +90 216 394 11 25 Fax: +90 216 394 11 24

E-mail: [info@farben.com.tr](mailto:info@farben.com.tr), [info@herkingroup.com](mailto:info@herkingroup.com)