



ALPINE TBA 550

Basification Agent

Appearance	: White powder
Characteristics	: Basification agent based on magnesium oxide

PROPERTIES AND APPLICATION:

- Alpine TBA 550 is obtained smooth chrome distribution in sections and surface, because of providing controlled pH rising. Chrome crash does not occur. It ensures high chromium uptake and chrome fixation.
- In the bath with slow dissolution provides much more controlled pH change.
- Do not form insoluble salts in the skin.
- It is obtained homogeneous dyeing with using Alpine TBA 550.
- It is added to chrome bath after penetration of chromium salts. Afterwards is rotated cabinet 6-8 hours.
- If it is used masking products in chrome tanning stage, Alpine TBA 550 should be added after about one hour from the masking product.

Recomended usage rates:

After chrome in chrome tanning 0,3 - 0,5 %

STORAGE :

In a cool and dry place in original packaging, can be stored for a period of one year. Product must be protected from excessive heat and cold.

PACKAGING :

25 kg bag.

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control not imply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.

FARBEN DERİ TEKSTİL KONFEKSİYON ve KİMYEVİ MAD. TİC. Ve SAN. A.Ş.

Organize Deri Sanayi Bölgesi 19. Yol 12/6 Parsel Aydınlı Köyü – Tuzla – İSTANBUL / TURKEY

Tel: +90 216 394 11 25 Fax: +90 216 394 11 24

E-mail: info@farben.com.tr, info@herkingroup.com