

FARBEN SHINE RETENAL CRN Aluminium Chrome Tanning Agent

Appearance	
Characteristics	
Al ₂ O ₃ (%)	
Cr ₂ O ₃ (%)	

- : Light greenish powder
- : Aluminium chrome tanning agent
- : 14,5
- : 3,5

PROPERTIES AND APPLICATION:

-It is used in tanning stage in the retannage of chrome tanned leather and fur production.

-It increases the penetration of mineral tanning.

-It is used in the production of white leather.

-It gives firmness to the skin to improve the structure of the leather fibers. It also ensures more uniform dyeing.

Recomended usage rates:

In chrome tanning	2,0 – 3,0 %
In retanning of white garment calf leather	2,0 – 4,0 %
In retanning of split suede leathers	6,0-8,0 %
In tanning of fur-suede	10,0 – 15,0 g/L
In chrome retanningof fur-suede	2,0 – 4,0 g/L

STORAGE :

In a cool and dry place in original packaging, can be stored for a period of one year. Product must be protected from excessive heat and cold.

PACKAGING :

25 kg bag

Technical information and recommendations contained herein, is reliable, but conditions and methods of use of our products are beyond our control notimply any warranty. We recommend to use to our customer after identified our products and the suitability of proposals of use. Tips on the use of our products be interpreted in terms of encouraging infringement of patent rights of others.